

TABLE I

	CIELAB optical values						Opacity	Ash content	Retention (one-pass)	Greying resistance	
	over white			over black							
	L*	a*	b*	L*	a*	b*	L [%]	[% by wt.]	[% by wt.]	$\Delta L^*$	$\Delta E^*$
Example 1	93.1	-1.2	2.6	90.9	-1.3	0.5	94.1	40.4	74	1.0	1.5
Comparative example 1	92.9	-1.2	2.8	90.2	-1.3	0.5	92.8	40.6	75	1.1	1.6
Comparative example 2	93.2	-1.2	2.5	90.9	-1.2	0.4	93.7	40.5	72	1.3	1.8

Coverage 100 grams/m<sup>2</sup> in all tests